

PAINTING OF CONCRETE FLOORS

2K EPOXY FLOOR PAINT

Mid Grey & Tile Red (RAL colours can be mixed at additional cost)

Items Needed:

- 2K Epoxy Floor Enamel (Sizes 5L)
- CP1500 Activator (Sizes 1L)
- Epoxy Thinner
- Acid Etch Solution (Sizes 5L, 20L)
- Floor rolling kit if needed (Solvent Resistant Sleeves)

INSTRUCTIONS

Power wash and Hoover/clean area to be free of dust and dirt.

Apply **Acid Etch Solution** to concrete floors that are very smooth or powerfloated. (This is applied using a deck scrub or hard bristle brush).

Wash out the remains of the Acid Etch Solution and wait 2 days for concrete to fully dry before painting.

First coat of 2K Epoxy Floor Paint should be mixed 4 parts paint to 1 part CP1500 activator – then thin by 20% Epoxy thinner.

Leave 24-48 hrs before applying second coat.

Second coat of 2K Epoxy Floor Paint should be mixed 4 parts paint to 1 part activator.

Paint will be fully cured after 5-7 days do not drive or use heavy machinery on floor within this time frame.

Do not apply Epoxy floor paint below 12 degrees.