


TECHNICAL DATA SHEET

Version 1.1 / 01.12.2019

Chlorinated Rubber

Product Description	Chlorinated Rubber is a flexible, hard wearing coating with good resistance to water in both acid and alkaline conditions. It is resistant to immersion in sea and fresh water but not recommended for drinking water tanks.												
Intended Use	It is particularly suitable in conditions where conventional paints may fail, e.g. Dairy Parlours, Silage pits and sewage installations. It can also be used as swimming pool paint on properly treated surfaces.												
Technical Data	<table><tr><td>Colours:</td><td>White, Blue, Grey and BS4800 and RAL colours</td></tr><tr><td>Finish:</td><td>Gloss Finish</td></tr><tr><td>Volume Solids:</td><td>40%</td></tr><tr><td>Film Thickness:</td><td>35 Microns dft</td></tr><tr><td>Practical Coverage:</td><td>Approx. 12 sqm/litre on smooth surfaces</td></tr><tr><td>VOC/Litre:</td><td>380g/litre</td></tr></table>	Colours:	White, Blue, Grey and BS4800 and RAL colours	Finish:	Gloss Finish	Volume Solids:	40%	Film Thickness:	35 Microns dft	Practical Coverage:	Approx. 12 sqm/litre on smooth surfaces	VOC/Litre:	380g/litre
Colours:	White, Blue, Grey and BS4800 and RAL colours												
Finish:	Gloss Finish												
Volume Solids:	40%												
Film Thickness:	35 Microns dft												
Practical Coverage:	Approx. 12 sqm/litre on smooth surfaces												
VOC/Litre:	380g/litre												
Surface Preparation	All surfaces must be clean, dry and free from all defective or poorly adhering material, dirt, grease and wax and be thoroughly rubbed down using suitable abrasive paper and dusted off. Remove all scale and rust by scraping with wire brushing or other conventional means. Previously painted surfaces should be tested by applying Chlorinated Rubber over a small test area and checking for softening or lifting of the old film.												
Application Details	<p>The normal recommended system is to apply two coats of Chlorinated Rubber paint with the first coat thinned approx 10% on new surfaces. When applying to steel apply a coat of Castle fast dry zinc phosphate primer before Chlorinated Rubber.</p> <p>Application Method: Brush or roller</p> <p>Thinner: Xylene (when required)</p>												
Drying Time	<table><tr><td>Substrate Temperature:</td><td>10°C</td></tr><tr><td>Touch Dry:</td><td>1 Hour</td></tr><tr><td>Hard Dry:</td><td>3 Hours</td></tr><tr><td>Minimum Overcoat:</td><td>2-3 Hours</td></tr><tr><td>Maximum Overcoat:</td><td>Unlimited</td></tr></table>	Substrate Temperature:	10°C	Touch Dry:	1 Hour	Hard Dry:	3 Hours	Minimum Overcoat:	2-3 Hours	Maximum Overcoat:	Unlimited		
Substrate Temperature:	10°C												
Touch Dry:	1 Hour												
Hard Dry:	3 Hours												
Minimum Overcoat:	2-3 Hours												
Maximum Overcoat:	Unlimited												



TECHNICAL DATA SHEET

Version 1.1 / 01.12.2019

Storage & Handling

Storage: Always store and transport in a secure upright position. Store the closed container in a cool dry place.

Keep away from extremes of temperature.

Pack Size: 1 Litre, 2.5 Litre, 5 Litre, 20 Litre.

Health & Safety

Paint product - flammable

Keep away from sources of ignition

Do not take internally

Keep out of the reach of children

In case of contact with eyes rinse immediately with plenty of water

In case of insufficient ventilation wear suitable respiratory equipment

Remove splashes from skin using soap and water or a recognised skin cleaner

Dispose of container and contents in accordance with local/national regulations

Do not empty product into drains or watercourses

See MSDS for more information

Quality Assurance

Castle Paints products are manufactured using only the highest quality raw materials. We guarantee the quality of our products. This guarantee does not include labour or cost of labour for the application of any paint.



The information contained herein is to the best of our knowledge true and accurate and is given in good faith but without warranty. The user will be deemed to have satisfied him/herself independently as to the suitability of our products for his/her own particular purpose. In no event shall Castle Paints be liable for consequential or incidental damages.